PROJECT T0607-3 Page 1 of 8

LABORATORY MEASUREMENT OF A PRE-CAST LIGHTWEIGHT CONCRETE PANEL WALL SYSTEM

(According to ISO 140-3)

Prepared for: Litecrete (NZ) Ltd

66 Boundary Rd

Papakura Auckland

Prepared by: Acoustics Testing Services

Department of Architecture

THE UNIVERSITY OF AUCKLAND

AUCKLAND UNISERVICES LTD
THE UNIVERSITY OF AUCKLAND
PRIVATE BAG 92019
AUCKLAND

Dr. G Dodd

Mr. Gian Schmid



PROJECT T0607-3 Page 2 of 8

Airborne sound reduction indices according to ISO 140-3 Laboratory measurements of airborne sound insulation of building elements

Description and identification of the test specimen and test arrangement:

Airbourne sound insulation of a lightweight pre-cast concrete wall

Date of test: 31-May-06

Litecrete (NZ) Ltd

Test Wall: Four 150mm thick lightweight pre-cast concrete panels of nominal size 2.3m x 1.28m, joints sealed with foam sealing rods and *Sika Firerate intrumescent fire rated joint sealant*. 25mm *USG Furring channels* fixed horizontally at 620mm centres in *RSIC clips* at 900mm centres.

Test Wall Lining: 13mm Gib Standard plasterboard screw-fixed at 300mm centres to the USG Furring

channels on Chamber A side only

Cavity Absorption: AUTEX AAB 35-25 polyester blanket.

Test Wall Lining Joint filler: Gib TradeSet 45 jointing compound

Test Wall Perimeter Sealer: Gib Soundseal

Chamber A and Chamber C were used respectively as receiving chambers in successive tests. Test specimen was installed by client. Curing time:18hrs

Computer Files: T0607-3 C-A T0607-3 C-A T0607-3 A-C T0607-3 A-C

90.00

Surface area of test specimen: 11.73 m²

Mass per unit area: 211.07 kg/m²

curve of ASTM E413 reference values.curve of ISO 717-1 reference values.

Test room air temperature: 16 °C
Test room relitive humidity: 67 %


R

Source room volume: 202-208 m³

Receiving room volume: 208-202 n

%	
m^3	
m^3	





Notes: #N/A = Value not available. **Bold** values are used to calculate STC and R_w .

Rating according to ISO 717-1

 $R_w (C;C_{tr}) = 59 (-3;-9) dB$

 $C_{50-3150} = -3 \text{ dB}$ $C_{tr,50-3150} = -11 \text{ dB}$ $C_{50-5000} = -2 \text{ dB}$ $C_{tr,50-5000} = -11 \text{ dB}$ $C_{100-5000} = -2 \text{ dB}$ $C_{\text{tr},100-5000} = -9 \text{ dB}$

Frequency, f, Hz

Rating according to ASTM E413 -87

87

4,100 0000

S.

Sound Transmission Class = 60 dB

Evaluation based on laboratory measurement results obtained by an engineering method.

No. of test report: T0607-3

Name of test institute: University of Auckland Acoustics Testing Service

Date:

Signature:



ANNEX A.


PHOTOS OF TEST SPECIMEN IN CHAMBER.



Figure 1: Chamber A side before the addition of Furring channels and plasterboard



PROJECT T0607-3 Page 4 of 8







INSTRUMENTATION	EQUIPMENT	TYPE / SERIAL No.	
	CHAMBER C SOURCE ROOM		
	1/2" Microphone	4165 / 1622303	
	Preamplifier	2619 / 945952	
	Rotating Boom	3923 / 936497	
	CHAMBER A RECEIVING ROOM		
	1/2" Microphone	4190 / 2150379	
	Preamplifier	2619 / 945949	
	Rotating Boom	3923 / 936496	
	Calibration of the above equipment was conducted by Electroacoustic Calibration Services (ECS), an IANZ registered laboratory.		
	BOTH ROOMS		
	Pistonphone	4220 / 1048366	
	Analyzer	01dB Stell / 01381	



PROJECT T0607-3 Page 6 of 8



INSTALLATION OF TEST SAMPLE

The wall under test is installed in the opening between two reverberation chambers – chambers C and A for a wall, chambers A and B for a floor. These chambers are vibration isolated from each other which results in a structural discontinuity at the middle of the test opening. This gap is covered over by a collar, which seals the gap and provides for ease of fixing of samples. The wall sample is constructed by the client following the techniques normally used in practice for that type of wall or floor/ceiling, and is sealed into the test opening with perimeter seals of acoustic sealant. For ease of removal, the surfaces of the test opening are covered with an adhesive, heavy fabric tape prior to the construction of the building element.

SOUND INSULATION OF BUILDING ELEMENTS.

METHOD

The measured transmission loss values are obtained in accordance with the recommendations of ISO standard 140-3:1995(E) "Laboratory Measurement of Airborne Sound Insulation of Building Elements."

Essentially the transmission loss of a building element is measured by generating sound on one side of the building element (the source chamber) and measuring how much sound is transmitted into the receiving chamber. In the source chamber pink noise is radiated from a loudspeaker. Time and space averaged sound pressure levels in both the source and receiving chambers are measured by using a rotating boom microphone, and the average sound pressure levels are obtained by sampling the sound pressure levels as the boom rotates through one cycle (taking 64 seconds). This is repeated for a different loudspeaker position in the source chamber.

Measurements of the background noise levels in the receiving chamber are also made. Then, should it prove necessary, the transmitted noise levels are corrected for the influence of background noise as prescribed in the standard.

The sound absorption of the receiving chamber is also determined by measuring the reverberation times (ISO-354:2003(E) "Measurement of Sound Absorption in a Reverberation Room").

RESULTS

The third octave band sound reduction indices R are presented in both table and graph formats. Sometimes a highly reflective test sample means that the lower frequency sound pressure levels cannot be reliably measured; this is indicated by #N/A in the table of results. Additionally, if the specimen is highly insulating, sometimes the background noise affects the measurements, resulting in only an upper threshold being found; this is indicated by a > sign preceding the tabulated results.

Single figure ratings are also presented. The weighted sound reduction index $R_{\rm W}$, determined according to ISO 717-1, is presented along with spectrum adaptation terms $C_{\rm Ir}$ and $C_{\rm Ir}$ and $C_{\rm Ir}$ will be negative, indicating the poor sound insulation at low frequency as low frequency and low frequency and low frequency and low frequency and low frequency range of 50Hz to 5000Hz. For light timber constructions at low frequencies.

The sound transmission class (STC) determined according ASTM E413 is also presented. This is determined by fitting a reference curve to the third octave band sound reduction indices R from 125Hz to 4000Hz, but in a slightly different way to ISO 717-2. The sound transmission class gives a single figure rating of the sound reduction through the building element so that higher is better.





THE ACOUSTICS RESEARCH CENTRE

There are three large interconnected reverberation chambers at the Acoustics Research Centre, two at ground level (Chambers C and A) and the third (Chamber B) below A.

All three reverberation chambers may be described as hexagonal prisms; each have 6 vertical sided walls, perpendicular to the floor. The roofs of chamber A and C are plane, but inclined at 12 degrees from horizontal. Chamber B has a plane, horizontal roof which is the floor of chamber A above it. The floor of chamber B is also horizontal, but has two angled sections at its north west and south east ends. The center section is horizontal because a floor jack is installed there. The floor jack may be raised hydraulically to the ceiling of chamber B, the centre of which consists of a floor plug between the two chambers. This plug may be disconnected from chamber A and lowered down into chamber B, leaving a 3.2m x 3.2 m opening between the two chambers. This allows for the measurement of airborne and impact insulation of floor and roof elements.

The wall of chamber C adjacent to chamber A is left open, and the corresponding wall of chamber A consists of a pair of iron doors that are clamped against the chamber. The clamps may be removed and the iron doors pulled back, leaving the entire wall area (4.6m wide x 2.74m high) between the chambers open. This allows for the measurement of airborne sound insulation of wall elements.

Chamber A has a rotating vane diffuser in a central position with an area (both sides) of about 53 m². It has the shape of two cones with their bases joined, with the two opposite quadrants of one cone open and the complementary quadrants in the other cone open. Chamber C has a similar rotating vane diffuser but it is smaller, having a total area of about 27 m².

In addition, up to ten static diffusers may be employed if needed. These are constructed of two laminated layers of dense formica, of dimensions 1m x 1m. The formica elements are riveted to a frame constructed of aluminium T section. Four aluminium arms may be bolted onto the frame to allow the diffusers to be mounted as desired.

Currently four of these are used in chamber C, and three are used in chamber B.

The volumes and surface areas of the reverberation chambers are as follows:

	VOLUME (m³)	SURFACE AREA (m²)
Chamber A	202 ± 3	203.6 ± 0.9
Chamber B	153 ± 2	173 ± 1
Chamber C	209 ± 4	214 ± 0.9



PROJECT T0607-3 Page 8 of 8

The three Reverberation Chambers are linked by heavy steel doors and a removable Standard Industrial Floor Section which is removed and repositionde by a hydrolic hoist. The three chambers are vibration isolated from one another so that sound can only pass from one to the other via the intervening Test Wall or Test Floor/Ceiling Section.

